Product Data Sheet



GRÜNPERGA Papier GmbH Am Güterbahnhof 3 09579 Grünhainichen Germany

- made from 100% virgin fibers

GRÜNPERGA - Coffee Filter paper unbleached

Characteristic:

- wet strength

- absorbent

Application:

- for coffee filters and basket filters
 - tea filter
 - transport and storage underlay for different food
 - many other application possibilities can be checked individually

									tolerance (absolute)
basisweight ISO 536	gsm	35	41	45	51	54	56	58	<u>+</u> 4%
moisture ISO 287	%	5,5							<u>+</u> 0,5
thickness (80 sheets) ISO 534	mm	6,7	7,2	7,7	9,2	9,7	10,2	10,2	<u>+</u> 0,5
tensile strength MD ISO 1924-2	Ν	<u>></u> 13	<u>></u> 15	<u>></u> 18	<u>></u> 23	<u>></u> 25	<u>></u> 27	<u>></u> 27	
tensile strength CD ISO 1924-2	Ν				<u>></u> 13	<u>></u> 14	<u>></u> 15	<u>></u> 15	
wet tensile strength MD ISO 3781	Ν	<u>></u> 2,0	<u>></u> 3,0		<u>≥</u> 4,0		<u>></u> 4,5		
wet tensile strength CD ISO 3781	Ν	≥ 2,5							
time of filtration (method HERZBERG)	S	25 - 40			30 - 45				

Properties of quality:

- odourless and tasteless

The paper grade is in compliance with the rules of

- Regulation (EC) No 1935/2004 of the European Parliament

- Foodstuffs, Consumer Goods and Animal Feed Code, LFGB §§ 30,31

and is approved according to the

- BfR Recommendation, Paper and board for food contact, XXXVI, XXXVI/1, XXXVI/2 and XXXVI/3

- Code of Federal Regulations, Food and Drugs (FDA) 21 CFR Ch. I §§ 176.170, 176.180

according to the ISEGA Certificate of Compliance No. 56960 U22

and is **compostable** according to the requirements of EN 13432 (test certificate No. 908 P 17)

Grünhainichen, February 2023